

Phillips 66 COPYLENE® CR350CS-01 Polypropylene Random Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

COPYLENE® CR350CS-01 is a clarified, reactor grade, random copolymer specially designed for clear injection molding applications and is formulated with lube for excellent mold release for larger articles. Applications: Injection Molding Information provided by Phillips 66.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Phillips-66-COPYLENE-CR350CS-01-Polypropylene-Random-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.902 g/cc	0.0326 lb/in ³	ASTM D792
Melt Flow	35 g/10 min @Load 2.16 kg, Temperature 230 °C	35 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	29.3 MPa	4250 psi	(2 in/min); ASTM D638
Elongation at Yield	13.5 %	13.5 %	ASTM D638
Flexural Modulus	1.07 GPa	155 ksi	0.05 in/mm, 1% Secant, Procedure A; ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	Method A; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	74.0 °C	165 °F	Unannealed; ASTM D648

Descriptive Properties	Value	Comments
Process	Injection Molding	
Region	Mexico	Bamberger Polymers Distribution
	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China