

## Phillips 66 COPYLENE® CR750CL-02 Polypropylene, Random Copolymer, NX-8000 based

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

### Material Notes:

COPYLENE™ CR750CL-02 is an easy molding, high melt flow random copolymer that has good see-through and contact clarity in injection molding applications and is formulated with advanced technology. Applications: Housewares, Clear containers  
Information provided by Phillips 66.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Phillips-66-COPYLENE-CR750CL-02-Polypropylene-Random-Copolymer-NX-8000-based.php](http://www.lookpolymers.com/polymer_Phillips-66-COPYLENE-CR750CL-02-Polypropylene-Random-Copolymer-NX-8000-based.php)

Physical Properties	Metric	English	Comments
Density	0.902 g/cc	0.0326 lb/in <sup>3</sup>	ASTM D792
Melt Flow	75 g/10 min @Load 2.16 kg, Temperature 230 °C	75 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	27.6 MPa	4000 psi	2 in/min; ASTM D638
Elongation at Yield	13 %	13 %	ASTM D638
Flexural Modulus	1.03 GPa	150 ksi	0.05 in/min; 1% secant; Procedure A; ASTM D790
Izod Impact, Notched	0.534 J/cm @Temperature 23.0 °C	1.00 ft-lb/in @Temperature 73.4 °F	Method A; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	78.0 °C	172 °F	unannealed; ASTM D648

Descriptive Properties	Value	Comments
Process	Injection Molding	
Region	Mexico	Bamberger Polymers Distribution
	US & Canada	Bamberger Polymers Distribution

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215, Fengxian District, Shanghai City, China**