

Pinnacle Polymers 1703 Polypropylene Homopolymer, Stretched Tape Grade

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Fiber Grade

Material Notes:

This Pinnacle Polymers Polypropylene is made via UNIPOL™ PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency. Features: Excellent color and processing stability Resistance to gas fading Low water carry-over Excellent lot-to-lot consistency Applications: Woven products Carpet backing Sacking Industrial and geotextile fabrics Certifications: Pinnacle's polypropylene, as marketed by Pinnacle Polymers Company, in natural, uncolored pellet form complies with appropriate requirements of CFR Title 21, Part 177, Subpart B, Section 177.1520 (c) 1.1a entitled "Olefin Polymers" of the Food Additives Amendment of 1958 to the United States Food, Drug and Cosmetic Act of 1938. Information provided by Pinnacle Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Pinnacle-Polymers-1703-Polypropylene-Homopolymer-Stretched-Tape-Grade.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	ASTM D1505
Melt Flow	3.5 g/10 min	3.5 g/10 min	Condition L 230/2.16; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	35.9 MPa @Thickness 3.20 mm	5200 psi @Thickness 0.126 in	At 51mm/min, injection molded ASTM Type 1 specimen; ASTM D638
Elongation at Yield	10 % @Thickness 3.20 mm	10 % @Thickness 0.126 in	At 51mm/min, injection molded ASTM Type 1 specimen; ASTM D638
Flexural Modulus	1.65 GPa @Thickness 3.20 mm	240 ksi @Thickness 0.126 in	At 1.27 mm/min, 1% secant, injection molded ASTM Type 1 specimen; ASTM D790A
Izod Impact, Notched	0.374 J/cm @Thickness 3.20 mm, Temperature 22.8 °C	0.700 ft-lb/in @Thickness 0.126 in, Temperature 73.0 °F	injection molded ASTM Type 1 specimen; ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China