

## Pinnacle Polymers 2135 Impact Polypropylene Copolymer, Injection Molding Grade

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

### Material Notes:

This Pinnacle Polymers Polypropylene is made via UNIPOL™ PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency. Features: Good impact strength High melt flow Superior processability Applications: Packaging Housewares Consumer products Certifications: Pinnacle's polypropylene, as marketed by Pinnacle Polymers Company, in natural, uncolored pellet form complies with appropriate requirements of CFR Title 21, Part 177, Subpart B, Section 177.1520 (c) 1.1a entitled "Olefin Polymers" of the Food Additives Amendment of 1958 to the United States Food, Drug and Cosmetic Act of 1938. Information provided by Pinnacle Polymers.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Pinnacle-Polymers-2135-Impact-Polypropylene-Copolymer-Injection-Molding-Grade.php](http://www.lookpolymers.com/polymer_Pinnacle-Polymers-2135-Impact-Polypropylene-Copolymer-Injection-Molding-Grade.php)

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in <sup>3</sup>	ASTM D1505
Melt Flow	35 g/10 min	35 g/10 min	Condition L 230/2.16; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	25.1 MPa @Thickness 3.20 mm	3640 psi @Thickness 0.126 in	At 51mm/min, injection molded ASTM Type 1 specimen; ASTM D638
Elongation at Yield	11 % @Thickness 3.20 mm	11 % @Thickness 0.126 in	At 51mm/min, injection molded ASTM Type 1 specimen; ASTM D638
Flexural Modulus	1.03 GPa @Thickness 3.20 mm	150 ksi @Thickness 0.126 in	At 1.27 mm/min, 1% secant, injection molded ASTM Type 1 specimen; ASTM D790A
Izod Impact, Notched	0.801 J/cm @Thickness 3.20 mm, Temperature 22.8 °C	1.50 ft-lb/in @Thickness 0.126 in, Temperature 73.0 °F	injection molded ASTM Type 1 specimen; ASTM D256

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China