

Plaskolite Optix® CA - 41 HF General Purpose Acrylic Resin

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, General Purpose, Molded , Acrylic, Optical Grade, Molded

Material Notes:

OPTIX® general purpose acrylics are available in a variety of performance grades that offer varying melt flow rates, heat resistance, color/opacity and gloss levels. Information provided by Plaskolite, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plaskolite-Optix-CA-41-HF-General-Purpose-Acrylic-Resin.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ASTM D-792
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	ASTM D-955
Melt Flow	32 g/10 min @Load 3.80 kg, Temperature 230 °C	32 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	74	74	ASTM D-785
Tensile Strength	53.0 MPa	7680 psi	ASTM D-638
Elongation at Break	2.4 %	2.4 %	ASTM D-638
Modulus of Elasticity	2.727 GPa	395.5 ksi	ASTM D-638
Flexural Strength	76.19 MPa	11050 psi	ASTM D-790
Izod Impact, Notched	0.160 J/cm @Thickness 6.35 mm	0.300 ft-lb/in @Thickness 0.250 in	ASTM D-256
Gardner Impact	0.226 J @Thickness 3.17 mm	0.167 ft-lb @Thickness 0.125 in	Falling Weight; ASTM D-3029 GB

Thermal Properties	Metric	English	Comments
CTE, linear	60.0 µm/m-°C	33.3 µin/in-°F	ASTM D-696
Deflection Temperature at 1.8 MPa (264 psi)	71.7 °C	161 °F	ASTM D-648
Vicat Softening Point	88.9 °C	192 °F	ASTM D-1525

Optical Properties	Metric	English	Comments
Haze	<= 1.0 %	<= 1.0 %	ASTM D-1003

Optical Properties

Metric

English

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China