

## Plaslok 5314 Black (COM) Impact Grade Phenolic Molding Compound (discontinued \*\*)

Category : Polymer , Thermoset , Phenolic , Phenolic, Novolac, Impact Grade, Filled

### Material Notes:

Plaslok Corporation was purchased by Plastics Engineering Company (maker of Plenco brand materials) in March 2000. The Plaslok name is no longer in use. Plaslok 5314 is the replacement material for the former Union Carbide BMMA-5314. It is a two-stage, impact grade phenolic molding compound suitable for compression, transfer or injection molding of parts where toughness is desired but surface finish is not a requirement. Data provided by Plaslok Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plaslok-5314-Black-COM-Impact-Grade-Phenolic-Molding-Compound-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Plaslok-5314-Black-COM-Impact-Grade-Phenolic-Molding-Compound-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in <sup>3</sup>	ASTM D792
Apparent Bulk Density	0.450 g/cc	0.0163 lb/in <sup>3</sup>	ASTM D1895
Water Absorption	0.80 %	0.80 %	ASTM D570
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	Compression; ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	46.0 MPa	6670 psi	ASTM D638
Flexural Yield Strength	62.0 MPa	8990 psi	ASTM D790
Flexural Modulus	6.90 GPa	1000 ksi	ASTM D790
Compressive Yield Strength	172 MPa	24900 psi	ASTM D695
Izod Impact, Notched	0.290 J/cm	0.543 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	160 °C	320 °F	ASTM D648
UL RTI, Electrical	150 °C @Thickness 1.57 mm	302 °F @Thickness 0.0618 in	
UL RTI, Mechanical with Impact	150 °C @Thickness 1.57 mm	302 °F @Thickness 0.0618 in	
UL RTI, Mechanical without Impact	150 °C @Thickness 1.57 mm	302 °F @Thickness 0.0618 in	

Flammability, UL 94 Thermal Properties	HB Metric	HB English	3.18mm Comments
	HB	HB	3.18mm

Electrical Properties	Metric	English	Comments
Electrical Resistivity	3.00e+11 ohm-cm	3.00e+11 ohm-cm	ASTM D257
Dielectric Constant	5.3	5.3	1MHz; ASTM D150
	8.5	8.5	60 Hz; ASTM D150
Dielectric Strength	13.2 kV/mm	335 kV/in	ASTM D149
Dissipation Factor	0.050	0.050	1 MHz; ASTM D150
	0.24	0.24	60 Hz; ASTM D150
Comparative Tracking Index	138 V	138 V	UL 746

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China