

## Plastcom SLOVALEN PC 51 T 30 Polypropylene Copolymer, 30% Micronized Talc

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer , Polypropylene with 30% Talc Filler

### Material Notes:

Features Modified copolymer PP for injection moulding with the content of 30% micronized, floated, chemically modified talc. General application in all industry branches - packing material, garden flower-pots, toys, furniture industry, dowels, clamps, hinge, office chairs, hangers, covers of car chassis, fenders, motors etc. Increased toughness. Delivered in natural and in the full RAL color scale. Application: Injection Moulding Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plastcom-SLOVALEN-PC-51-T-30-Polypropylene-Copolymer-30-Micronized-Talc.php](http://www.lookpolymers.com/polymer_Plastcom-SLOVALEN-PC-51-T-30-Polypropylene-Copolymer-30-Micronized-Talc.php)

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in <sup>3</sup>	STN 64 0111
Linear Mold Shrinkage	0.0212 cm/cm	0.0212 in/in	STN 64 0808
Linear Mold Shrinkage, Transverse	0.0196 cm/cm	0.0196 in/in	STN 64 0808
Melt Flow	5.0 g/10 min @Load 2.16 kg, Temperature 230 °C	5.0 g/10 min @Load 4.76 lb, Temperature 446 °F	STN EN ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	30.0 MPa	4350 psi	STN EN ISO 527-2
Elongation at Break	4.0 %	4.0 %	STN EN ISO 527-2
Tensile Modulus	2.80 GPa	406 ksi	STN EN ISO 527-2
Flexural Strength	80.0 MPa	11600 psi	STN EN ISO 178
Flexural Modulus	2.40 GPa	348 ksi	STN EN ISO 178
Charpy Impact Unnotched	1.50 J/cm <sup>2</sup> @Temperature -20.0 °C	7.14 ft-lb/in <sup>2</sup> @Temperature -4.00 °F	STN EN ISO 179
	5.00 J/cm <sup>2</sup> @Temperature 23.0 °C	23.8 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	STN EN ISO 179
Charpy Impact, Notched	0.300 J/cm <sup>2</sup> @Temperature -20.0 °C	1.43 ft-lb/in <sup>2</sup> @Temperature -4.00 °F	STN EN ISO 179
	0.400 J/cm <sup>2</sup> @Temperature 23.0 °C	1.90 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	STN EN ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	150 °C	302 °F	DSC; STN EN ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	130 °C	266 °F	STN EN ISO 75/A
Vicat Softening Point	90.0 °C	194 °F	B; STN EN ISO 306

Processing Properties	Metric	English	Comments
Melt Temperature	200 - 250 °C	392 - 482 °F	
Mold Temperature	40.0 - 60.0 °C	104 - 140 °F	
Injection Pressure	70.0 - 120 MPa	10200 - 17400 psi	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China