

Plastcom SLOVALEN PC 63 T 15-1M PP, 15% mineral filling

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler , Polypropylene with 20% Talc Filler

Material Notes:

Features Modified PP copolymer for injection moulding with the content of 15 % mineral filler, uv stabilized, good scratch resistance, low odor and very good flowability with good dimensional stability. The grade is designed for molding of automotive interior trims. Delivered in natural form or in colormatched form. Packaging, transport, stocking The product is packed in hermetically closed thick-walled 25 kg PE bags, on a 1.000 kg palette coated in a stretch foil, in big bags with a thick PE foil fixed on a 1.000 kg palette, in paper octabins with a thick PE foil fixed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation. Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastcom-SLOVALEN-PC-63-T-15-1M-PP-15-mineral-filling.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in ³	
Melt Flow	8.0 g/10 min	8.0 g/10 min	
	@Load 0.325 kg, Temperature 270 °C	@Load 0.716 lb, Temperature 518 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	18.0 MPa	2610 psi	
Elongation at Break	25 %	25 %	
Tensile Modulus	1.50 GPa	218 ksi	
Flexural Strength	17.0 MPa	2470 psi	
Flexural Modulus	1.45 GPa	210 ksi	
Charpy Impact Unnotched	NB	NB	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	NB	NB	
	@Temperature -20.0 °C	@Temperature -4.00 °F	
Charpy Impact, Notched	0.500 J/cm ²	2.38 ft-lb/in ²	
	@Temperature -20.0 °C	@Temperature -4.00 °F	
Charpy Impact, Notched	1.40 J/cm ²	6.66 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	52.0 °C	126 °F	
Vicat Softening Point	105 °C	221 °F	B
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Melt Temperature	200 - 250 °C	392 - 482 °F	
Mold Temperature	40.0 - 50.0 °C	104 - 122 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	4 hour	4 hour	
Injection Pressure	70.0 - 120 MPa	10200 - 17400 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China