

Plastcom SLOVALEN PH 59 GF 30 PP, 30% glass fibre

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

Material Notes:

Features Modified homopolymer PP for injection moulding, chemically reinforced with 30% glass fibre, with high strength, rigidity and toughness, adapted thermal properties, decreased shrinkage. Suitable for automotive, engineering, electrical and consumer goods industry. With the increasing content of GF also the toughness, tensile and bending strength, modulus in tension and bending increase and the shrinkage decreases as well as the heat application increases up to 150°C. Additional drying of the material is not necessary. Delivered in natural mode and in the full RAL colour scale. Production of the fuel tank caps for the transport vehicles, shells for the textile industry. Packaging, transport, stocking The product is packed in hermetically closed thick-walled 25 kg PE bags, on a 1.000 kg palette coated in a stretch foil, in big bags with a thick PE foil fixed on a 1.000 kg palette, in paper octabins with a thick PE foil fixed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation. Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastcom-SLOVALEN-PH-59-GF-30-PP-30-glass-fibre.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	
Linear Mold Shrinkage	0.0072 cm/cm	0.0072 in/in	
Linear Mold Shrinkage, Transverse	0.0082 cm/cm	0.0082 in/in	
Melt Flow	6.0 g/10 min @Load 0.325 kg, Temperature 270 °C	6.0 g/10 min @Load 0.716 lb, Temperature 518 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	80.0 MPa	11600 psi	
Elongation at Break	30 %	30 %	
Tensile Modulus	5.65 GPa	819 ksi	
Flexural Strength	128 MPa	18600 psi	
Flexural Modulus	4.89 GPa	709 ksi	
Charpy Impact Unnotched	4.50 J/cm ² @Temperature -20.0 °C	21.4 ft-lb/in ² @Temperature -4.00 °F	
	5.00 J/cm ² @Temperature 23.0 °C	23.8 ft-lb/in ² @Temperature 73.4 °F	

Mechanical Properties	0.900 J/cm ² Metric	4.28 ft-lb/in ² English	Comments
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	1.10 J/cm ²	5.23 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	160 °C	320 °F	
Deflection Temperature at 1.8 MPa (264 psi)	134 °C	273 °F	
Vicat Softening Point	162 °C	324 °F	B
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Melt Temperature	200 - 250 °C	392 - 482 °F	
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	2 hour	2 hour	
Injection Pressure	70.0 - 120 MPa	10200 - 17400 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China