

Plastcom SLOVALEN PH 91 GF 15 Polypropylene Homopolymer, 15% Glass Fiber

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler

Material Notes:

Features Modified homopolymer PP for injection moulding, chemically reinforced with 15% glass fiber, with high strength, rigidity and toughness, adapted thermal properties, decreased shrinkage. Suitable for automotive, engineering, electrical and consumer goods industry. With the increasing content of GF also the toughness, tensile and bending strength, modulus in tension and bending increase and the shrinkage decreases as well as the heat application increases up to 130°C. Additional drying of the material is not necessary. Delivered in natural and in the full RAL color scale. Application: Injection Moulding Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastcom-SLOVALEN-PH-91-GF-15-Polypropylene-Homopolymer-15-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	STN 64 0111
Linear Mold Shrinkage	0.0188 cm/cm	0.0188 in/in	STN 64 0808
Linear Mold Shrinkage, Transverse	0.020 cm/cm	0.020 in/in	STN 64 0808
Melt Flow	15 g/10 min @Load 2.16 kg, Temperature 230 °C	15 g/10 min @Load 4.76 lb, Temperature 446 °F	STN EN ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	40.0 MPa	5800 psi	STN EN ISO 527-2
Elongation at Break	4.0 %	4.0 %	STN EN ISO 527-2
Tensile Modulus	3.30 GPa	479 ksi	STN EN ISO 527-2
Flexural Strength	60.0 MPa	8700 psi	STN EN ISO 178
Flexural Modulus	2.20 GPa	319 ksi	STN EN ISO 178
Charpy Impact Unnotched	2.00 J/cm ² @Temperature -20.0 °C	9.52 ft-lb/in ² @Temperature -4.00 °F	STN EN ISO 179
	5.00 J/cm ² @Temperature 23.0 °C	23.8 ft-lb/in ² @Temperature 73.4 °F	STN EN ISO 179
Charpy Impact, Notched	0.100 J/cm ² @Temperature -20.0 °C	0.476 ft-lb/in ² @Temperature -4.00 °F	STN EN ISO 179
	1.40 J/cm ²	6.66 ft-lb/in ²	STN EN ISO 179

Mechanical Properties	@Temperature 23.0 °C Metric	@Temperature 73.4 °F English	Comments
Thermal Properties	Metric	English	Comments
Melting Point	160 °C	320 °F	DSC; STN EN ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	STN EN ISO 75/A
Vicat Softening Point	130 °C	266 °F	B; STN EN ISO 306
Processing Properties	Metric	English	Comments
Melt Temperature	200 - 250 °C	392 - 482 °F	
Mold Temperature	40.0 - 60.0 °C	104 - 140 °F	
Injection Pressure	70.0 - 120 MPa	10200 - 17400 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China