

Plastcom SLOVALEN PQ 83 T 40 PP, 40% mineral filling

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Talc Filler

Material Notes:

Features Modified PP for injection moulding with the content of 40% mineral filling, uv stabilized. Increased rigidity, strength and thermal use up to 130°C depending on the talc content. Decreased shrinkage. General application in all industry branches - packing material, garden flower-pots, toys, furniture industry, dowels, clamps, hinge, office chairs, hangers, covers of car chassis, fenders, motors, wheels cover, etc. Packaging, transport, stocking The product is packed in hermetically closed thick-walled 25 kg PE bags, on a 1.000 kg palette coated in a stretch foil, in big bags with a thick PE foil fixed on a 1.000 kg palette, in paper octabins with a thick PE foil fixed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation. Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastcom-SLOVALEN-PQ-83-T-40-PP-40-mineral-filling.php

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in ³	
Linear Mold Shrinkage	0.0095 cm/cm	0.0095 in/in	
Linear Mold Shrinkage, Transverse	0.011 cm/cm	0.011 in/in	
Melt Flow	8.0 g/10 min @Load 0.325 kg, Temperature 270 °C	8.0 g/10 min @Load 0.716 lb, Temperature 518 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	17.0 MPa	2470 psi	
Elongation at Break	10 %	10 %	
Tensile Modulus	1.75 GPa	254 ksi	
Flexural Strength	21.0 MPa	3050 psi	
Flexural Modulus	1.50 GPa	218 ksi	
Charpy Impact Unnotched	6.40 J/cm ²	30.5 ft-lb/in ²	
	@Temperature -20.0 °C	@Temperature -4.00 °F	
Charpy Impact, Notched	NB	NB	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.400 J/cm ²	1.90 ft-lb/in ²	
	@Temperature -20.0 °C	@Temperature -4.00 °F	

Mechanical Properties	Metric	English	Comments
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	56.0 °C	133 °F	
Vicat Softening Point	60.0 °C	140 °F	B
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Melt Temperature	200 - 250 °C	392 - 482 °F	
Mold Temperature	40.0 - 50.0 °C	104 - 122 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	4 hour	4 hour	
Moisture Content	0.20 %	0.20 %	
Injection Pressure	70.0 - 120 MPa	10200 - 17400 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China