

## Plastcom SLOVAMID 6 FRB 4 LS Polyamide 6, Halogen Free Flame Retardant, Light Stabilization

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Unreinforced, Flame Retardant

### Material Notes:

Features PA 6 for injection moulding with increased flammability resistance with non-halogen flame retardant. Determined for electrical purposes. Excellent flow of the material predetermines it for the manufacturing of complicated small as well as large surface mouldings. Possible for wall thickness from 0.5mm. High grade surface brightness also at colored types. Delivered in natural and in the full RAL color scale. Application: Injection Moulding Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plastcom-SLOVAMID-6-FRB-4-LS-Polyamide-6-Halogen-Free-Flame-Retardant-Light-Stabilization.php](http://www.lookpolymers.com/polymer_Plastcom-SLOVAMID-6-FRB-4-LS-Polyamide-6-Halogen-Free-Flame-Retardant-Light-Stabilization.php)

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	STN 64 0111
Linear Mold Shrinkage	0.0145 cm/cm	0.0145 in/in	STN 64 0808
Linear Mold Shrinkage, Transverse	0.0152 cm/cm	0.0152 in/in	STN 64 0808
Melt Flow	10 g/10 min @Load 2.16 kg, Temperature 230 °C	10 g/10 min @Load 4.76 lb, Temperature 446 °F	STN EN ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	STN EN ISO 527-2
Elongation at Break	4.0 %	4.0 %	STN EN ISO 527-2
Tensile Modulus	2.75 GPa	399 ksi	STN EN ISO 527-2
Flexural Strength	95.0 MPa	13800 psi	STN EN ISO 178
Flexural Modulus	3.00 GPa	435 ksi	STN EN ISO 178
Charpy Impact Unnotched	5.00 J/cm <sup>2</sup> @Temperature -20.0 °C	23.8 ft-lb/in <sup>2</sup> @Temperature -4.00 °F	STN EN ISO 179
	5.50 J/cm <sup>2</sup> @Temperature 23.0 °C	26.2 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	STN EN ISO 179
Charpy Impact, Notched	0.300 J/cm <sup>2</sup> @Temperature -20.0 °C	1.43 ft-lb/in <sup>2</sup> @Temperature -4.00 °F	STN EN ISO 179
	0.400 J/cm <sup>2</sup> @Temperature 23.0 °C	1.90 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	STN EN ISO 179

Mechanical Properties	Metric	English	Comments
Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	DSC; STN EN ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	60.0 °C	140 °F	STN EN ISO 75/A
Vicat Softening Point	200 °C	392 °F	B; STN EN ISO 306
Flammability, UL94	V-0	V-0	
Glow Wire Test	960 °C	1760 °F	STN IEC 60695-2-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	STN IEC 60093
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	STN IEC 60093
Dielectric Strength	20.0 kV/mm	508 kV/in	STN IEC 60243
Comparative Tracking Index	500 V	500 V	STN 34 6468

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 270 °C	482 - 518 °F	
Mold Temperature	50.0 - 70.0 °C	122 - 158 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	4 hour	4 hour	
Moisture Content	0.15 %	0.15 %	STN EN ISO 960
Injection Pressure	70.0 - 100 MPa	10200 - 14500 psi	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China