

Plastcom SLOVAMID 6 FRM 2 PA6, flame retardant

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced, Flame Retardant

Material Notes:

FeaturesDetermined for electrotechnical use. Delivered in natural mode. PA 6 for injection moulding with reduced flammability, with nonhalogen flame retardant. Excellent fluidity of the material predetermines it for the manufacturing of complicated small and large surface mouldings. Possible use for products with wall thickness from 0.5 mm. High grade brightness also at coloured types. Delivered in the full RAL colour scale.Packaging, transport, stockingThe product is packed in hermetically closed thick-walled 25 kg PE bags, on a 1.000 kg palette coated in a stretch foil, in big bags with a thick PE foil fixed on a 1.000 kg palette, in paper octabins with a thick PE foil fixed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation.Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastcom-SLOVAMID-6-FRM-2-PA6-flame-retardant.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	
Viscosity Measurement	1.15 - 1.43	1.15 - 1.43	
Linear Mold Shrinkage	0.0143 cm/cm	0.0143 in/in	
Linear Mold Shrinkage, Transverse	0.0115 cm/cm	0.0115 in/in	
Melt Flow	10 g/10 min @Load 0.325 kg, Temperature 270 °C	10 g/10 min @Load 0.716 lb, Temperature 518 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	75.0 MPa	10900 psi	
Elongation at Break	4.0 %	4.0 %	
Tensile Modulus	3.00 GPa	435 ksi	
Flexural Strength	100 MPa	14500 psi	
Flexural Modulus	2.50 GPa	363 ksi	
Charpy Impact Unnotched	16.0 J/cm ² @Temperature -20.0 °C	76.1 ft-lb/in ² @Temperature -4.00 °F	
	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	
	0.200 J/cm ²	0.952 ft-lb/in ²	

Charpy Impact, Notched Mechanical Properties	Metric @ Temperature -20.0 °C	English @ Temperature -4.00 °F	Comments
	0.250 J/cm ²	1.19 ft-lb/in ²	
	@ Temperature 23.0 °C	@ Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	
Deflection Temperature at 1.8 MPa (264 psi)	60.0 °C	140 °F	
Vicat Softening Point	200 °C	392 °F	B
Flammability, UL94	V-0	V-0	
Glow Wire Test	960 °C	1760 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	
Dielectric Strength	20.0 kV/mm	508 kV/in	
Comparative Tracking Index	500 V	500 V	

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 270 °C	482 - 518 °F	
Mold Temperature	50.0 - 70.0 °C	122 - 158 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	4 hour	4 hour	
Moisture Content	0.15 %	0.15 %	
Injection Pressure	70.0 - 100 MPa	10200 - 14500 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China