

Plastcom SLOVAMID 6 GF 10 FRC 2 PA6, 10% glass fibre, flame retardant

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 10% Glass Fiber Filled , Nylon 6, Glass Fiber Filled, Flame Retardant

Material Notes:

Features PA 6 for injection moulding, chemically strengthened with 10 % glass fibre. Application: impacted mouldings and mouldings with high strength applied in automotive, electrical, engineering and consumer-goods industry, eg.: grips for electro tools, hobby tools, gears, cases of the electro tools, cooling screws of blowers, electromotors, carrying parts in the automotive industry. With the increasing content of GF also the toughness, bending and tensile strength increase as well as the heat application increases up to 250°C and the shrinkage decreases. Delivered in natural mode and in the full RAL colour scale. Packaging, transport, stocking The product is packed in hermetically closed thick-walled 25 kg PE bags, on a 1.000 kg palette coated in a stretch foil, in big bags with a thick PE foil fixed on a 1.000 kg palette, in paper octabins with a thick PE foil fixed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation. Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastcom-SLOVAMID-6-GF-10-FRC-2-PA6-10-glass-fibre-flame-retardant.php

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in ³	
Viscosity Measurement	0.67 - 1.58	0.67 - 1.58	
Linear Mold Shrinkage	0.0067 cm/cm	0.0067 in/in	
Linear Mold Shrinkage, Transverse	0.0158 cm/cm	0.0158 in/in	
Melt Flow	3.0 g/10 min	3.0 g/10 min	
	@Load 0.325 kg, Temperature 270 °C	@Load 0.716 lb, Temperature 518 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	90.0 MPa	13100 psi	
Elongation at Break	4.0 %	4.0 %	
Tensile Modulus	5.80 GPa	841 ksi	
Flexural Strength	160 MPa	23200 psi	
Flexural Modulus	4.80 GPa	696 ksi	
Charpy Impact Unnotched	2.00 J/cm ²	9.52 ft-lb/in ²	
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	2.50 J/cm ²	11.9 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Mechanical Properties	Metric /cm ²	English -lb/in ²	Comments
Charpy Impact, Notched	@Temperature -20.0 °C	@Temperature -4.00 °F	
	0.300 J/cm ²	1.43 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	
Vicat Softening Point	200 °C	392 °F	B
Flammability, UL94	V-2	V-2	
Glow Wire Test	850 °C	1560 °F	

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 270 °C	482 - 518 °F	
Mold Temperature	70.0 - 80.0 °C	158 - 176 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	4 hour	4 hour	
Moisture Content	0.15 %	0.15 %	
Injection Pressure	70.0 - 120 MPa	10200 - 17400 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China