

Plastcom SLOVAMID 6 T 20 PA6, 20% mineral filling

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 20% Mineral Filled

Material Notes:

Features Decreased shrinkage against the BT types, increased heat application up to 170°C. Increased modulus in tension - strength of the material. PA matrix reduction. Application eg. for tools, filling-in dowells. PA for injection moulding with the content of 20% micromilled talc. Delivered in natural mode and in the full RAL colour scale. Packaging, transport, stocking The product is packed in hermetically closed thick-walled 25 kg PE bags, on a 1.000 kg palette coated in a stretch foil, in big bags with a thick PE foil fixed on a 1.000 kg palette, in paper octabins with a thick PE foil fixed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation. Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastcom-SLOVAMID-6-T-20-PA6-20-mineral-filling.php

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in ³	
Viscosity Measurement	0.79 - 0.82	0.79 - 0.82	
Linear Mold Shrinkage	0.0082 cm/cm	0.0082 in/in	
Linear Mold Shrinkage, Transverse	0.0079 cm/cm	0.0079 in/in	
Melt Flow	3.0 g/10 min	3.0 g/10 min	
	@Load 0.325 kg, Temperature 270 °C	@Load 0.716 lb, Temperature 518 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	105 MPa	15200 psi	
Elongation at Break	9.0 %	9.0 %	
Tensile Modulus	5.20 GPa	754 ksi	
Flexural Strength	95.0 MPa	13800 psi	
Flexural Modulus	4.80 GPa	696 ksi	
Charpy Impact Unnotched	2.00 J/cm ²	9.52 ft-lb/in ²	
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	4.00 J/cm ²	19.0 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.200 J/cm ²	0.952 ft-lb/in ²	

Mechanical Properties	@Temperature -20.0 °C Metric	@Temperature -4.00 °F English	Comments
	0.400 J/cm ²	1.90 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	
Vicat Softening Point	200 °C	392 °F	B
Flammability, UL94	HB	HB	
Glow Wire Test	650 °C	1200 °F	

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 270 °C	482 - 518 °F	
Mold Temperature	50.0 - 70.0 °C	122 - 158 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	4 hour	4 hour	
Moisture Content	0.15 %	0.15 %	
Injection Pressure	70.0 - 120 MPa	10200 - 17400 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China