

Plastcom SLOVAMID 6 T 30 Polyamide 6, 30% Micronized Talc

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Mineral Filled

Material Notes:

Features Decreased shrinkage against the BT types, increased heat application up to 170°C. Increased tensile modulus - strength of the material. PA matrix reduction. Application for tools, filling-in dowels. PA for injection moulding with the content of 30% micronized talc. Delivered in natural and in the full RAL color scale. Application: Injection Moulding Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastcom-SLOVAMID-6-T-30-Polyamide-6-30-Micronized-Talc.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	STN 64 0111
Linear Mold Shrinkage	0.0085 cm/cm	0.0085 in/in	STN 64 0808
Linear Mold Shrinkage, Transverse	0.0084 cm/cm	0.0084 in/in	STN 64 0808
Melt Flow	15 g/10 min @Load 2.16 kg, Temperature 230 °C	15 g/10 min @Load 4.76 lb, Temperature 446 °F	STN EN ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	85.0 MPa	12300 psi	STN EN ISO 527-2
Elongation at Break	5.0 %	5.0 %	STN EN ISO 527-2
Tensile Modulus	5.15 GPa	747 ksi	STN EN ISO 527-2
Flexural Strength	110 MPa	16000 psi	STN EN ISO 178
Flexural Modulus	3.85 GPa	558 ksi	STN EN ISO 178
Charpy Impact Unnotched	3.00 J/cm ² @Temperature -20.0 °C	14.3 ft-lb/in ² @Temperature -4.00 °F	STN EN ISO 179
	4.50 J/cm ² @Temperature 23.0 °C	21.4 ft-lb/in ² @Temperature 73.4 °F	STN EN ISO 179
Charpy Impact, Notched	0.300 J/cm ² @Temperature -20.0 °C	1.43 ft-lb/in ² @Temperature -4.00 °F	STN EN ISO 179
	0.700 J/cm ² @Temperature 23.0 °C	3.33 ft-lb/in ² @Temperature 73.4 °F	STN EN ISO 179

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Melting Point Thermal Properties	220 °C Metric	428 °F English	DSC: STN EN ISO 3146 Comments
Deflection Temperature at 1.8 MPa (264 psi)	120 °C	248 °F	STN EN ISO 75/A
Vicat Softening Point	225 °C	437 °F	B; STN EN ISO 306
Flammability, UL94	HB	HB	
Glow Wire Test	650 °C	1200 °F	STN IEC 60695-2-10

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 270 °C	482 - 518 °F	
Mold Temperature	50.0 - 70.0 °C	122 - 158 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	4 hour	4 hour	
Moisture Content	0.15 %	0.15 %	STN EN ISO 960
Injection Pressure	70.0 - 120 MPa	10200 - 17400 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China