

## Plastcom SLOVAMID 66 GF 30 FRA 5 Polyamide 66, 30% Glass Fiber, Halogen Flame Retardant

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Glass Fiber Filled, Flame Retardant

### Material Notes:

Features PA 66 for injection moulding, reinforced with 30% glass fiber and halogen flame retardant. Application in electrical industry: breakers, coil forms, covers, terminals. Slightly decreased flammability, glow wire 960°C. Application: Injection Moulding Information  
Provided by Plastcom spol. s r.o.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plastcom-SLOVAMID-66-GF-30-FRA-5-Polyamide-66-30-Glass-Fiber-Halogen-Flame-Retardant.php](http://www.lookpolymers.com/polymer_Plastcom-SLOVAMID-66-GF-30-FRA-5-Polyamide-66-30-Glass-Fiber-Halogen-Flame-Retardant.php)

Physical Properties	Metric	English	Comments
Density	1.49 g/cc	0.0538 lb/in <sup>3</sup>	STN 64 0111
Linear Mold Shrinkage	0.0048 cm/cm	0.0048 in/in	STN 64 0808
Linear Mold Shrinkage, Transverse	0.0085 cm/cm	0.0085 in/in	STN 64 0808
Melt Flow	1.0 g/10 min @Load 2.16 kg, Temperature 230 °C	1.0 g/10 min @Load 4.76 lb, Temperature 446 °F	STN EN ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	150 MPa	21800 psi	STN EN ISO 527-2
Elongation at Break	2.0 %	2.0 %	STN EN ISO 527-2
Tensile Modulus	9.50 GPa	1380 ksi	STN EN ISO 527-2
Flexural Strength	220 MPa	31900 psi	STN EN ISO 178
Flexural Modulus	7.60 GPa	1100 ksi	STN EN ISO 178
Charpy Impact Unnotched	5.00 J/cm <sup>2</sup> @Temperature -20.0 °C	23.8 ft-lb/in <sup>2</sup> @Temperature -4.00 °F	STN EN ISO 179
	5.50 J/cm <sup>2</sup> @Temperature 23.0 °C	26.2 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	STN EN ISO 179
Charpy Impact, Notched	0.900 J/cm <sup>2</sup> @Temperature -20.0 °C	4.28 ft-lb/in <sup>2</sup> @Temperature -4.00 °F	STN EN ISO 179
	1.00 J/cm <sup>2</sup> @Temperature 23.0 °C	4.76 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	STN EN ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	DSC; STN EN ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	250 °C	482 °F	STN EN ISO 75/A
Vicat Softening Point	250 °C	482 °F	B; STN EN ISO 306
Flammability, UL94	V-0	V-0	
Glow Wire Test	960 °C	1760 °F	STN IEC 60695-2-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+17 ohm-cm	1.00e+17 ohm-cm	STN IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	STN IEC 60093
Dielectric Strength	40.0 kV/mm	1020 kV/in	STN IEC 60243
Comparative Tracking Index	450 V	450 V	STN 34 6468

Processing Properties	Metric	English	Comments
Melt Temperature	280 - 300 °C	536 - 572 °F	
Mold Temperature	70.0 - 90.0 °C	158 - 194 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	4 hour	4 hour	
Moisture Content	0.15 %	0.15 %	STN EN ISO 960
Injection Pressure	70.0 - 120 MPa	10200 - 17400 psi	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China