

## Plastcom SLOVAMID 66 GF 50 LS PA66, 50% glass fibre, light stability

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 50% Glass Fiber Filled

### Material Notes:

Features Chemically reinforced with 50% glass fibre, suitable for mouldings with high strength and toughness also at minus temperatures. Used in the automotive, engineering and electrical industry, light stable. Application: hobby tools, covers of electrotools, electromotors, cooling screws of blowers, gear wheels, carrying parts in the automotive industry like eg. brake cables. Delivered in natural mode and in the full RAL colour scale. Packaging, transport, stocking The product is packed in hermetically closed thick-walled 25 kg PE bags, on a 1.000 kg palette coated in a stretch foil, in big bags with a thick PE foil fixed on a 1.000 kg palette, in paper octabins with a thick PE foil fixed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation. Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plastcom-SLOVAMID-66-GF-50-LS-PA66-50-glass-fibre-light-stability.php](http://www.lookpolymers.com/polymer_Plastcom-SLOVAMID-66-GF-50-LS-PA66-50-glass-fibre-light-stability.php)

Physical Properties	Metric	English	Comments
Density	1.55 g/cc	0.0560 lb/in <sup>3</sup>	
Viscosity Measurement	0.56 - 0.93	0.56 - 0.93	
Linear Mold Shrinkage	0.0056 cm/cm	0.0056 in/in	
Linear Mold Shrinkage, Transverse	0.0093 cm/cm	0.0093 in/in	
Melt Flow	3.0 g/10 min @Load 0.325 kg, Temperature 270 °C	3.0 g/10 min @Load 0.716 lb, Temperature 518 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	230 MPa	33400 psi	
Elongation at Break	2.0 %	2.0 %	
Tensile Modulus	16.0 GPa	2320 ksi	
Flexural Strength	300 MPa	43500 psi	
Flexural Modulus	14.0 GPa	2030 ksi	
Charpy Impact Unnotched	8.00 J/cm <sup>2</sup> @Temperature -20.0 °C	38.1 ft-lb/in <sup>2</sup> @Temperature -4.00 °F	
	9.00 J/cm <sup>2</sup> @Temperature 23.0 °C	42.8 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	
	1.20 J/cm <sup>2</sup>	5.71 ft-lb/in <sup>2</sup>	

Charpy Impact, Notched Mechanical Properties	Metric @ Temperature -20.0 °C	English @ Temperature -4.00 °F	Comments
	1.40 J/cm <sup>2</sup>	6.66 ft-lb/in <sup>2</sup>	
	@ Temperature 23.0 °C	@ Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	
Deflection Temperature at 1.8 MPa (264 psi)	250 °C	482 °F	
Vicat Softening Point	250 °C	482 °F	B
Flammability, UL94	HB	HB	
Glow Wire Test	650 °C	1200 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Strength	90.0 kV/mm	2290 kV/in	
Comparative Tracking Index	575 V	575 V	

Processing Properties	Metric	English	Comments
Melt Temperature	280 - 300 °C	536 - 572 °F	
Mold Temperature	80.0 - 90.0 °C	176 - 194 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	4 hour	4 hour	
Moisture Content	0.15 %	0.15 %	
Injection Pressure	70.0 - 120 MPa	10200 - 17400 psi	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China