

Plastcom SLOVASTER® B GF 30 FRL 4 Polybutylene Terephthalate, 30% Chemically Coupled Glass Fiber, Bromine Hydrocarbon Flame Retardant

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled , Polybutylene Terephthalate (PBT), Flame Retardant

Material Notes:

Features PBT with the content of 30% chemically coupled glass fiber and flame retardant based on bromine hydrocarbons. Anisotropy of shrinkage enables injection moulding of round, cylindrical or other hole products. Application in engineering, electrical and automotive industry. High mechanical properties also in conditioned state. Delivered in natural and in the full RAL color scale. Application: Injection Moulding Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastcom-SLOVASTER-B-GF-30-FRL-4-Polybutylene-Terephthalate-30-Chemically-Coupled-Glass-Fiber-Bromine-Hydrocarbon-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Density	1.73 g/cc	0.0625 lb/in ³	STN 64 0111
Linear Mold Shrinkage	0.0111 cm/cm	0.0111 in/in	STN 64 0808
Linear Mold Shrinkage, Transverse	0.0168 cm/cm	0.0168 in/in	STN 64 0808
Melt Flow	5.0 g/10 min @Load 2.16 kg, Temperature 230 °C	5.0 g/10 min @Load 4.76 lb, Temperature 446 °F	STN EN ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	130 MPa	18900 psi	STN EN ISO 527-2
Elongation at Break	2.0 %	2.0 %	STN EN ISO 527-2
Tensile Modulus	10.5 GPa	1520 ksi	STN EN ISO 527-2
Flexural Strength	180 MPa	26100 psi	STN EN ISO 178
Flexural Modulus	9.00 GPa	1310 ksi	STN EN ISO 178
Charpy Impact Unnotched	5.00 J/cm ² @Temperature 23.0 °C	23.8 ft-lb/in ² @Temperature 73.4 °F	STN EN ISO 179
	5.00 J/cm ² @Temperature -20.0 °C	23.8 ft-lb/in ² @Temperature -4.00 °F	STN EN ISO 179
Charpy Impact, Notched	0.900 J/cm ² @Temperature 23.0 °C	4.28 ft-lb/in ² @Temperature 73.4 °F	STN EN ISO 179
	0.900 J/cm ²	4.28 ft-lb/in ²	STN EN ISO 179

Mechanical Properties	@Temperature -20.0 °C Metric	@Temperature -4.00 °F English	Comments
Thermal Properties	Metric	English	Comments
Melting Point	200 - 220 °C	392 - 428 °F	DSC; STN EN ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	STN EN ISO 75/A
Vicat Softening Point	210 °C	410 °F	B; STN EN ISO 306
Flammability, UL94	V-0	V-0	
Glow Wire Test	960 °C	1760 °F	STN IEC 60695-2-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+17 ohm-cm	1.00e+17 ohm-cm	STN IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	STN IEC 60093
Dielectric Strength	32.0 kV/mm	813 kV/in	STN IEC 60243
Comparative Tracking Index	50 V	50 V	STN 34 6468

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 280 °C	482 - 536 °F	
Mold Temperature	50.0 - 90.0 °C	122 - 194 °F	
Drying Temperature	120 °C	248 °F	
Dry Time	4 hour	4 hour	
Moisture Content	0.050 %	0.050 %	STN EN ISO 960
Injection Pressure	60.0 - 100 MPa	8700 - 14500 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China