

PlastiComp Complet® LCF50 - PP Homopolymer Polypropylene, 50% Long Carbon Fiber Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Carbon Fiber Filled

Material Notes:

Complet® long-fiber reinforced pellets are manufactured to exceed expectation for quality and performance. Polypropylene with 50% carbon fiber reinforcement. Information provided by PlastiComp, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PlastiComp-Complet-LCF50-PP-Homopolymer-Polypropylene-50-Long-Carbon-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.23 g/cc	1.23 g/cc	ASTM D-792
Filler Content	50 %	50 %	Carbon Fiber

Mechanical Properties	Metric	English	Comments
Tensile Strength	86.0 MPa	12500 psi	ASTM D-638
Elongation at Break	1.0 %	1.0 %	ASTM D-638
Tensile Modulus	22.138 GPa	3210.9 ksi	ASTM D-638
Flexural Strength	157 MPa	22800 psi	ASTM D-790
Flexural Modulus	19.31 GPa	2801 ksi	ASTM D-790
Izod Impact, Unnotched	3.738 J/cm	7.003 ft-lb/in	ASTM D-4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	135 °C	275 °F	ASTM D-648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	199 - 210 °C	390 - 410 °F	
Middle Barrel Temperature	204 - 216 °C	400 - 420 °F	
Front Barrel Temperature	210 - 221 °C	410 - 430 °F	
Nozzle Temperature	204 - 216 °C	400 - 420 °F	
Melt Temperature	210 - 221 °C	410 - 430 °F	
Mold Temperature	79.4 °C	175 °F	

Injection Velocity Processing Properties	50.8 - 76.2 mm/sec Metric	2.00 - 3.00 in/sec English	Comments
Back Pressure	0.172 - 0.345 MPa	25.0 - 50.0 psi	
Cushion	0.635 cm	0.250 in	
Screw Speed	30 - 50 rpm	30 - 50 rpm	

Descriptive Properties	Value	Comments
Injection Pressure	Medium to maximum	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China