

Plastics Group Polifil® GFPP-10 10% Glass-Reinforced Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Glass Fiber Filler

Material Notes:

Polifil® GFPP series compounds are homopolymer polypropylene resins reinforced with glass fibers. They provide high impact with increased strength, stiffness, surface hardness, and higher continuous temperature. Other benefits include reduced distortion under long-term stress. Applications: Appliances Electrical components Automotive Utility products Standard processing techniques are applicable.

Information provided by The Plastics Group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastics-Group-Polifil-GFPP-10-10-Glass-Reinforced-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.980 g/cc	0.0354 lb/in ³	ASTM D792
Filler Content	10 %	10 %	ASTM D2584
Linear Mold Shrinkage	0.0050 cm/cm @Thickness 1.59 mm	0.0050 in/in @Thickness 0.0625 in	ASTM D955
Melt Flow	8.0 - 12 g/10 min	8.0 - 12 g/10 min	230/2.16; May be specified; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	39.3 MPa	5700 psi	ASTM D638
Flexural Strength	51.0 MPa	7400 psi	ASTM D638
Flexural Modulus	2.34 GPa	340 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	At 73°F; ASTM D256
Gardner Impact	0.904 J	0.667 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	135 °C	275 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China