

## Plastics Group Polifil® GFPP-30 30% Glass-Reinforced Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

### Material Notes:

Polifil® GFPP series compounds are homopolymer polypropylene resins reinforced with glass fibers. They provide high impact with increased strength, stiffness, surface hardness, and higher continuous temperature. Other benefits include reduced distortion under long-term stress. Applications: Appliances Electrical components Automotive Utility products Standard processing techniques are applicable.

Information provided by The Plastics Group.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plastics-Group-Polifil-GFPP-30-30-Glass-Reinforced-Polypropylene.php](http://www.lookpolymers.com/polymer_Plastics-Group-Polifil-GFPP-30-30-Glass-Reinforced-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in <sup>3</sup>	ASTM D792
Filler Content	30 %	30 %	ASTM D2584
Linear Mold Shrinkage	0.0030 cm/cm @Thickness 1.59 mm	0.0030 in/in @Thickness 0.0625 in	ASTM D955
Melt Flow	8.0 - 12 g/10 min	8.0 - 12 g/10 min	230/2.16; May be specified; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	49.0 MPa	7100 psi	ASTM D638
Flexural Strength	72.4 MPa	10500 psi	ASTM D638
Flexural Modulus	4.27 GPa	620 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.641 J/cm	1.20 ft-lb/in	At 73°F; ASTM D256
Gardner Impact	0.451 J	0.333 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	145 °C	293 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China