Plastics Group Polifil® RP-ABS Acrylonitrile-Butadiene Styrene, High Flow Version

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Polifil® RP- Acrylonitrile-Butadiene Styrene is a styrenic resin with improved toughness and heat resistance versus HIPS grades. ABS exhibits high gloss, low shrinkage, and good dimensional stability. ABS is widely used in injection molding of appliances, furniture, and automotive parts. ABS also has high melt strength suitable for the production of extruded sheet, some of considerable size and thickness. Applications include panels for large appliances and thermoformed items such as hot tubs and recreational vehicle parts. Information provided by The Plastics Group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastics-Group-Polifil-RP-ABS-Acrylonitrile-Butadiene-Styrene-High-Flow-Version.php

| Physical Properties | Metric | English | Comments |
|---------------------|-------------------|-------------------|------------------------------|
| Density | 1.06 g/cc | 0.0383 lb/in³ | ASTM D792 |
| Water Absorption | 0.20 % | 0.20 % | 24 hours; ASTM D570 |
| Melt Flow | 8.0 - 10 g/10 min | 8.0 - 10 g/10 min | 230/3.8, nominal; ASTM D1238 |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|-----------|---------------|----------------------|
| Tensile Strength, Yield | 35.9 MPa | 5200 psi | ASTM D638 |
| Elongation at Break | 20 % | 20 % | ASTM D638 |
| Flexural Modulus | 2.07 GPa | 300 ksi | 1% Secant; ASTM D790 |
| Izod Impact, Notched | 1.33 J/cm | 2.50 ft-lb/in | ASTM D256 |

| Thermal Properties | Metric | English | Comments |
|-----------------------|---------|---------|-----------|
| Vicat Softening Point | 98.9 °C | 210 °F | ASTM D648 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China