

## PlastxWorld CEVIAN® B5722 10% GF PBT/ABS Alloy

Category : Polymer , Thermoplastic , ABS Polymer , ABS/Polyester Alloy + GF , Polyester, TP , Polybutylene Terephthalate (PBT)

### Material Notes:

Glass fiber reinforced, heat resistant and flame retarded PBT/ABS alloy. Information provided by PlastxWorld Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PlastxWorld-CEVIAN-B5722-10-GF-PBTABS-Alloy.php](http://www.lookpolymers.com/polymer_PlastxWorld-CEVIAN-B5722-10-GF-PBTABS-Alloy.php)

Physical Properties	Metric	English	Comments
Density	1.39 g/cc	0.0502 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	70.3 MPa	10200 psi	ASTM D638
Elongation at Break	2.6 %	2.6 %	ASTM D638
Flexural Yield Strength	119 MPa	17200 psi	ASTM D790
Flexural Modulus	4.81 GPa	697 ksi	ASTM D790
Izod Impact, Notched	0.374 J/cm @Thickness 3.17 mm	0.700 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	205 °C	401 °F	0.25 inch; ASTM D648
UL RTI, Electrical	140 °C	284 °F	UL746B
UL RTI, Mechanical with Impact	100 °C	212 °F	UL746B
UL RTI, Mechanical without Impact	130 °C	266 °F	UL746B
Flammability, UL94	V-0 @Thickness 1.50 mm	V-0 @Thickness 0.0591 in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China