

## PlastxWorld CEVIAN® CGF20 20% GF PC/Acrylic Alloy

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic/Polycarbonate Alloy, Glass Fiber Filler , Polycarbonate (PC)

**Material Notes:**

Glass fiber reinforced PC/Acrylic alloy. These are typical values and are not intended for specification purposes. Information provided by PlastxWorld Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PlastxWorld-CEVIAN-CGF20-20-GF-PCAcrylic-Alloy.php](http://www.lookpolymers.com/polymer_PlastxWorld-CEVIAN-CGF20-20-GF-PCAcrylic-Alloy.php)

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in <sup>3</sup>	ASTM D792
Melt Flow	0.90 g/10 min @Load 3.80 kg, Temperature 230 °C	0.90 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	84.1 MPa	12200 psi	ASTM D638
Flexural Yield Strength	118 MPa	17100 psi	ASTM D790
Flexural Modulus	3.52 GPa	510 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm @Thickness 6.35 mm	1.30 ft-lb/in @Thickness 0.250 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	0.25 inch; ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China