

PlastxWorld Veroplas PA2000 Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

general purpose, unfilled injection molding grade Information provided by PlastxWorld Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PlastxWorld-Veroplas-PA2000-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM A792
Moisture Absorption at Equilibrium	<= 0.17 %	<= 0.17 %	Karl Fischer
Linear Mold Shrinkage	0.024 cm/cm	0.024 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	64.8 MPa	9400 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Flexural Yield Strength	80.0 MPa	11600 psi	ASTM D790
Flexural Modulus	2.70 GPa	392 ksi	ASTM D790
Izod Impact, Notched	0.502 J/cm	0.940 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	49.0 °C	120 °F	ASTM D648
Vicat Softening Point	182 °C	360 °F	ASTM D1525
Glow Wire Test	649 °C	1200 °F	UNE 20-672-83

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China