

PlastxWorld Veroplas PA2002MI Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

general purpose, unfilled, medium impact modified injection molding gradeInformation provided by PlastxWorld Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PlastxWorld-Veroplas-PA2002MI-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.11 g/cc	0.0401 lb/in ³	ASTM A792
Moisture Absorption at Equilibrium	<= 0.17 %	<= 0.17 %	Karl Fischer
Linear Mold Shrinkage	0.025 cm/cm	0.025 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	55.2 MPa	8000 psi	ASTM D638
Elongation at Break	45 %	45 %	ASTM D638
Flexural Yield Strength	64.8 MPa	9400 psi	ASTM D790
Flexural Modulus	1.80 GPa	261 ksi	ASTM D790
Izod Impact, Notched	3.00 J/cm	5.62 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	49.0 °C	120 °F	ASTM D648
Vicat Softening Point	171 °C	340 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China