

## PlastxWorld Veroplas PB3400 Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , 40% Glass Fiber Filled

**Material Notes:**

general purpose, 40% glass filled injection molding grade Information provided by PlastxWorld Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PlastxWorld-Veroplas-PB3400-Nylon-66.php](http://www.lookpolymers.com/polymer_PlastxWorld-Veroplas-PB3400-Nylon-66.php)

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in <sup>3</sup>	ASTM A792
Moisture Absorption at Equilibrium	<= 0.17 %	<= 0.17 %	Karl Fischer
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	190 MPa	27600 psi	ASTM D638
Elongation at Break	2.5 %	2.5 %	ASTM D638
Flexural Yield Strength	240 MPa	34800 psi	ASTM D790
Flexural Modulus	8.00 GPa	1160 ksi	ASTM D790
Izod Impact, Notched	1.77 J/cm	3.31 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	229 °C	444 °F	ASTM D648
Vicat Softening Point	249 °C	480 °F	ASTM D1525
Glow Wire Test	649 °C	1200 °F	UNE 20-672-83

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China