

## Plenco 308 Black (COM) Mineral/Flock Filled Phenolic Molding Compound (discontinued \*\*)

Category: Polymer, Thermoset, Filled/Reinforced Thermoset, Phenolic, Novolac, Mineral/Flock Filled

## **Material Notes:**

Plaslok 308 is a two-stage, mineral and flock-filled phenolic molding compound designed to withstand the hostile environment of high abrasion and high tangential speed of engine pulleys. It is characterized by both exceptional strength and good surface appearance. Data provided by Plaslok Corporation. Plaslok Corporation was purchased by Plastics Engineering Company in March 2000. The Plaslok name is no longer used on any products.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Plenco-308-Black-COM-MineralFlock-Filled-Phenolic-Molding-Compound-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.46 g/cc	0.0527 lb/in <sup>3</sup>	ASTM D792
Apparent Bulk Density	0.500 g/cc	0.0181 lb/in³	ASTM D1895
Water Absorption	0.40 %	0.40 %	ASTM D570
Linear Mold Shrinkage	0.0045 cm/cm	0.0045 in/in	Compression; ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	52.0 MPa	7540 psi	ASTM D638
Flexural Yield Strength	83.0 MPa	12000 psi	ASTM D790
Flexural Modulus	6.90 GPa	1000 ksi	ASTM D790
Compressive Yield Strength	166 MPa	24100 psi	ASTM D695
Izod Impact, Notched	0.290 J/cm	0.543 ft-lb/in	ASTM D256

Electrical Properties	Metric	English	Comments
Electrical Resistivity	2.20e+10 ohm-cm	2.20e+10 ohm-cm	ASTM D257
Dielectric Strength	12.2 kV/mm	310 kV/in	ASTM D149
Comparative Tracking Index	180 V	180 V	UL 746

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842



Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China