

## Plenco 51240 PET, Pellet, Injection Molded, Natural Color (discontinued \*\*)

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), Recycled, Glass Reinforced

### Material Notes:

PLENCO 51240 is an engineering grade glass reinforced flame retarded recycled polyethylene terephthalate resin designed for excellent dimensional stability. It is UL listed. Information supplied by PlencoPlenco discontinued their PET product line in 2005.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plenco-51240-PET-Pellet-Injection-Molded-Natural-Color-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Plenco-51240-PET-Pellet-Injection-Molded-Natural-Color-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.79 g/cc	0.0647 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.020 %	0.020 %	ASTM D570
Linear Mold Shrinkage	0.00060 cm/cm	0.00060 in/in	ATM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	115.1 MPa	16690 psi	ASTM D638
Elongation at Break	1.6 %	1.6 %	ASTM D638
Tensile Modulus	10.76 GPa	1561 ksi	ASTM D638
Flexural Yield Strength	176.1 MPa	25540 psi	ASTM D790
Flexural Modulus	10.33 GPa	1498 ksi	ASTM D790
Compressive Yield Strength	143.6 MPa	20830 psi	ASTM D695
Izod Impact, Notched	0.690 J/cm	1.29 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	220 °C	428 °F	ASTM D648
Flammability, UL94	V-0 @Thickness 1.47 mm	V-0 @Thickness 0.0579 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	8.71e+15 ohm-cm	8.71e+15 ohm-cm	ASTM D257
Dielectric Constant	3.8 @Frequency 1e+6 Hz	3.8 @Frequency 1e+6 Hz	ASTM D150
Dielectric Strength	16.7 kV/mm	424 kV/in	Short Time; ASTM D149

Electrical Properties	Metric	English	Comments
Dissipation Factor	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	ASTM D150
Arc Resistance	30 sec	30 sec	ASTM D495
Comparative Tracking Index	225 V	225 V	ASTM D3638

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China