

## Plenco 7507 Phenolic, Granular, Compression Molded

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Phenolic , Phenolic, Resole, Wood Filled

**Material Notes:**

PLENCO 07507 is an organic reinforced phenolic molding compound offering improved dimensional stability under humid conditions. 07507 offers excellent resistance to degradation from detergent solutions at elevated temperature. UL recognized under component file E40654. 07507 is available in black. Information supplied by Plenco.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plenco-7507-Phenolic-Granular-Compression-Molded.php](http://www.lookpolymers.com/polymer_Plenco-7507-Phenolic-Granular-Compression-Molded.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.600 g/cc	0.0217 lb/in <sup>3</sup>	ASTM D1895
Density	1.54 g/cc	0.0556 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.41 %	0.41 %	ASTM D570
Linear Mold Shrinkage	0.0037 cm/cm	0.0037 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell E	72	72	ASTM D785
Tensile Strength, Ultimate	54.0 MPa	7830 psi	ASTM D638
Elongation at Break	0.76 %	0.76 %	ASTM D638
Tensile Modulus	9.40 GPa	1360 ksi	ASTM D638
Flexural Strength	74.0 MPa	10700 psi	ASTM D790
Flexural Modulus	8.60 GPa	1250 ksi	ASTM D790
Compressive Strength	177 MPa	25700 psi	ASTM D695
Izod Impact, Notched	0.189 J/cm	0.354 ft-lb/in	ASTM D256
Charpy Impact, Notched	0.208 J/cm <sup>2</sup>	0.990 ft-lb/in <sup>2</sup>	ASTM D256
Impact	110	110	J/m Drop Ball Impact; PLENCO

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	207 °C	405 °F	Heat Resistance; ASTM D570D
Deflection Temperature at 1.8 MPa (264 psi)	216 °C	421 °F	ASTM D648
Flammability, UL94	V-1	V-1	

Thermal Properties	@Thickness 1.50 mm Metric	@Thickness 0.0591 in English	Comments
Shrinkage	0.38 %	0.38 %	72 hr, 120°C; ASTM D1299

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.60e+13 ohm-cm	1.60e+13 ohm-cm	ASTM D247
Dielectric Constant	5.8	5.8	ASTM D150
Dielectric Strength	13.2 kV/mm	335 kV/in	Short Time; ASTM D149
Dissipation Factor	0.051	0.051	ASTM D150
Arc Resistance	183 sec	183 sec	ASTM D495
Comparative Tracking Index	175 V	175 V	ASTM D3638

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China