

Poco Graphite CZR Semiconductor Grade Graphite

Category : Carbon , Graphite

Material Notes:

Although it is impossible to identify differences between various grades of graphite by looking at them, each grade has a special set of characteristics and physical properties that determine their performance under specific conditions. The manufacturing process for each grade is tightly controlled to produce materials that have a uniform microstructure and the right balance of strength, grain size and hardness to offer optimum performance for their intended applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Poco-Graphite-CZR-Semiconductor-Grade-Graphite.php

Physical Properties	Metric	English	Comments
Apparent Bulk Density	1.65 g/cc	0.0596 lb/in ³	
Particle Size	6.0 µm	6.0 µm	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	68	68	
Tensile Strength, Yield	38.0 MPa	5510 psi	Estimated at 70% of flexural strength
Flexural Strength	55.0 MPa	7980 psi	
Compressive Strength	105 MPa	15200 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	7.80 µm/m-°C	4.33 µin/in-°F	
Thermal Conductivity	76.0 W/m-K	527 BTU-in/hr-ft ² -°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00190 ohm-cm	0.00190 ohm-cm	

Descriptive Properties	Value	Comments
Oxidation Threshold	420°C	Temperature that results in 1% weight loss in 24 hours. Oxidation threshold increases by approximately 100°C if graphite is purified.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China