

Polimeri Europa Dutral® TER 6148 Ethylene - Propylene - Diene Terpolymer

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE)

Material Notes:

Dutral® TER 6148 is an Ethylene - Propylene - Diene polymer produced by suspension polymerization using a Ziegler-Natta Catalyst. A non-staining antioxidant is added during the production process. Key Features: Dutral® elastomers are characterized by excellent resistance to ageing and weathering, good resistance to both high an low temperatures, low permanent set values, good resistance to a large number of chemicals. Dutral® TER 6148 is an amorphous high molecular weight terpolymer of medium-high diene content, extended with 15% paraffinic oil. It is characterized by very good loading capacity and improved mixing processability, especially in medium and highly plasticized compounds. Dutral® TER 6148 based compounds present excellent low temperature performance, fast extrusion rate, fast curing, good shape stability and mechanical properties. Main Applications: Automotive, mechanical goods, building, appliances. Information provided by Polimeri Europa.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-Dutral-TER-6148-Ethylene-Propylene-Diene-Terpolymer.php

| Physical Properties | Metric | English | Comments |
|---------------------|---------------------|---------------------|----------|
| Volatiles | <= 0.50 % | <= 0.50 % | |
| Mooney Viscosity | 65 | 65 | |
| | @Temperature 125 °C | @Temperature 257 °F | |
| Ash | <= 0.30 % | <= 0.30 % | |

| Descriptive Properties | Value | Comments | |
|------------------------|--------|----------------------------|--|
| ENB Content | 7% wt | Referred to polymer matrix | |
| Oil Content | 15% wt | | |
| Propylene Content | 40% wt | Referred to polymer matrix | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China