

Polimeri Europa EDISTIR N1460 Polystyrene (discontinued **)

Category : Polymer , Thermoplastic , Polystyrene (PS)

Material Notes:

Symbol according to ISO 1043-1: PS Designation: Thermoplastic ISO 1622-PS,E,085-03 High molecular weight general purpose polystyrene with good mechanical strength. This grade is especially recommended for in-line thermoforming of disposable packaging and for sheet extrusion in blend with conventional or clear high impact polystyrene. Applications: Particularly suitable for thermoformed crystal clear cold-drink beakers, for clear egg trays and , in blend with HIPS, for dairy cups.Unfilled. Suitable for Sheet Extrusion, Thermoforming. Supplied as pellets.ISO data. Information provided by EnichemPolimeri Europa now has Enichem's plastics businesses. This grade is no longer in the product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-EDISTIR-N1460-Polystyrene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	
Melt Flow	3.0 g/10 min @Load 5.00 kg, Temperature 200 °C	3.0 g/10 min @Load 11.0 lb, Temperature 392 °F	cm ³ /10 min

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	41.0 MPa	5950 psi	5 mm/min
Elongation at Break	2.0 %	2.0 %	5 mm/min
Tensile Modulus	3.25 GPa	471 ksi	1 mm/min
Charpy Impact Unnotched	1.50 J/cm ²	7.14 ft-lb/in ²	
Charpy Impact, Notched	0.300 J/cm ²	1.43 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	79.0 °C	174 °F	
Vicat Softening Point	90.0 °C	194 °F	50°C/hr; 50N
Glass Transition Temp, Tg	89.0 °C	192 °F	10°C/min test
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Optical Properties	Metric	English	Comments
	80 %	80 %	Manufacturer specifies 'transparent'

Transmission Visible Optical Properties	Metric	English	but doesn't quantify. Comments
Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	
Dielectric Constant	2.5 @Frequency 100 Hz	2.5 @Frequency 100 Hz	
Dielectric Strength	70.0 kV/mm	1780 kV/in	
Dissipation Factor	0.00020 @Frequency 100 Hz	0.00020 @Frequency 100 Hz	
Comparative Tracking Index	400 V	400 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China