

Polimeri Europa Edistir RT 441M Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

High impact polystyrene combining high toughness and high stiffness with good flowability for easy processing. Designed for injection moulding of technical parts, housings and covers. Especially recommended for gas assisted technology. RT 441M is certified BSI 415/94 acc. IEC65-20-2 at 2.5 mm. Designation: Thermoplastics ISO 2897-PS-I,M,088-06-07-18 Applications: Business machine covers, electrical appliances, electroventilator housings, consumer electronics, front frames, cabinet and back cover for TV sets. RT 441M is certified UL94 HB "all colors" at 1.5 mm (UL file E83071). This grade in its natural version complies by composition with the requirements set by the main Regulations for plastic materials intended for food contact (including the EEC Directive 90/128 and subsequent amendments). Information provided by Polimeri Europa

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-Edistir-RT-441M-Polystyrene.php

Physical Properties	Metric	English	Comments
Bulk Density	0.650 g/cc	0.0235 lb/in ³	ISO 60
Density	1.04 g/cc	0.0376 lb/in ³	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	24 hours - 23°C; ISO 62
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	Internal Method
Melt Flow	7.5 g/10 min @Load 5.00 kg, Temperature 200 °C	7.5 g/10 min @Load 11.0 lb, Temperature 392 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	75	75	ISO 2039/2
Tensile Strength at Break	24.0 MPa	3480 psi	50 mm/min; ISO 527
Tensile Strength, Yield	22.0 MPa	3190 psi	50 mm/min; ISO 527
Elongation at Break	60 %	60 %	50 mm/min; ISO 527
Tensile Modulus	2.00 GPa	290 ksi	1 mm/min; ISO 527
Flexural Strength	45.0 MPa	6530 psi	2 mm/min; ISO 178
Izod Impact, Notched	1.10 J/cm @Thickness 3.20 mm, Temperature 23.0 °C	2.06 ft-lb/in @Thickness 0.126 in, Temperature 73.4 °F	ISO 180/4A
Izod Impact, Notched (ISO)	6.00 kJ/m ² @Thickness 4.00 mm,	2.86 ft-lb/in ² @Thickness 0.157 in,	ISO 180/1A

Mechanical Properties	Temperature -30.0 °C Metric	Temperature -22.0 °F English	Comments
	8.00 kJ/m ²	3.81 ft-lb/in ²	
	@Thickness 4.00 mm, Temperature 23.0 °C	@Thickness 0.157 in, Temperature 73.4 °F	ISO 180/1A

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 µm/m-°C	50.0 µin/in-°F	ASTM D 696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Thermal Conductivity	0.170 W/m-K	1.18 BTU-in/hr-ft ² -°F	ISO 8302
Deflection Temperature at 1.8 MPa (264 psi)	84.0 °C	183 °F	120°C/h; ASTM D 648
Vicat Softening Point	89.0 °C	192 °F	50 N - 50°C/h; ISO 306/B
	97.0 °C	207 °F	10 N - 50°C/h; ISO 306/A
Flammability, UL94	HB	HB	UL94
	@Thickness 1.50 mm	@Thickness 0.0591 in	
Glow Wire Test	650 °C	1200 °F	IEC 60695-2-1
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	7.00e+15 ohm-cm	7.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.50e+15 ohm	1.50e+15 ohm	IEC 60093
Dielectric Constant	2.5	2.5	IEC 60250
	@Frequency 50 Hz	@Frequency 50 Hz	
Dielectric Strength	65.0 kV/mm	1650 kV/in	IEC 60243
Dissipation Factor	0.00030	0.00030	IEC 60250
	@Frequency 50 Hz	@Frequency 50 Hz	
Comparative Tracking Index	500 V	500 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	210 - 260 °C	410 - 500 °F	Injection Molding
Mold Temperature	20.0 - 60.0 °C	68.0 - 140 °F	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China