

## Polimeri Europa Eraclene® ML 70 High Density Polyethylene - Injection Molding

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Injection Molded

### Material Notes:

Eraclene ML 70 is a high density polyethylene resin (HDPE) with antioxidants, suitable for injection molding application. Its narrow molecular weight distribution leads to high mechanical properties (rigidity, impact strength) together with high stress cracking resistance. Main Applications: Eraclene ML 70 is suggested to produce items with high mechanical performances, industrial containers, pallets and lids for open drums. Information provided by Polimeri Europa.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polimeri-Europa-Eraclene-ML-70-High-Density-Polyethylene-Injection-Molding.php](http://www.lookpolymers.com/polymer_Polimeri-Europa-Eraclene-ML-70-High-Density-Polyethylene-Injection-Molding.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.951 g/cc	0.951 g/cc	ISO 1183
Melt Flow	2.8 g/10 min	2.8 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	
	8.0 g/10 min	8.0 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 190 °C	@Load 11.0 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	64	64	ISO 868/A
Tensile Strength at Break	20.0 MPa	2900 psi	ISO 527
Tensile Strength, Yield	25.0 MPa	3630 psi	ISO 527
Elongation at Break	800 %	800 %	ISO 527
Flexural Modulus	1.10 GPa	160 ksi	ISO 178
Izod Impact, Notched	2.00 J/cm	3.75 ft-lb/in	ISO 180/A

Thermal Properties	Metric	English	Comments
Melting Point	135 °C	275 °F	Internal method
Vicat Softening Point	125 °C	257 °F	ISO 306/A
	@Load 1.00 kg	@Load 2.20 lb	
Brittleness Temperature	<= -60.0 °C	<= -76.0 °F	ASTM D746

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**