

Polimeri Europa Extir Leonardo A 7000 AE Expandable Polystyrene (discontinued **)

Category : Polymer , Thermoplastic , Polystyrene (PS) , Expanded Polystyrene (EPS)

Material Notes:

Extir A 7000 AE is a flame retardant expandable polystyrene in the form of spherical beads of large particle size, containing pentane as blowing agent. Extir does not contain CFC or HCFC. Extir A 7000 AE is suitable for production of low density blocks for the thermal insulation sector. Applications: Extir A 7000 AE is used mainly in the construction sector where, for legislative or safety reasons, the use of a flame retardant material is required. Typical applications are: • low density blocks, especially for external thermal insulation • low density elastified blocks for impact sound absorption (Trittschall) • blocks or slabs for road foundations and civil construction It is recommended to keep the product in a dry well ventilated store between 15-20°C. For product packaged in octabins the guaranteed shelf-life is one month; product in steel drums has a six months guaranteed shelf-life. During the processing of Expandable Polystyrene any sparkle or flame must be avoided and smoking should be forbidden. An adequate electrical grounding of machinery and of pneumatic transport lines is recommended. For further information concerning storage, packaging and processing precautions please refer to "Styrenics - Technical data sheets" and to the "Extir Safety Data Sheet". Regarding "flame retardant" properties, articles made from Extir AE are officially certified "B1 nach DIN 4102". The action of the flame retardant additive is exerted only after the elimination of blowing agent and, therefore, only after Extir AE has been transformed into foamed articles (suitably aged where necessary). Processing: Extir A 7000 AE can be easily pre-expanded down to 15 kg/m³ after one expansion and down to 11 kg/m³ after a second one. The recommended ageing time before moulding obviously depends on the preexpanded density and ranges from 6 to 48 hours. Moulding is characterised by fast cycle times. In addition, due to an excellent reaction to steam, it is possible to mould with a higher content of FR recycled material without significant reductions in properties. Blocks are cut into sheets of the desired thickness or into shaped articles by means of hot and/or oscillating wires. Information provided by Polimeri Europa

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-Extir-Leonardo-A-7000-AE-Expandable-Polystyrene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Bulk Density	0.590 - 0.630 g/cc	0.0213 - 0.0228 lb/in ³	
Density	0.0110 - 0.0200 g/cc	0.000397 - 0.000723 lb/in ³	
Apparent Bulk Density	0.0100 g/cc	0.000361 lb/in ³	On a continuous pre-expander after two expansions
	0.0120 g/cc	0.000434 lb/in ³	On a discontinuous pre-expander
	0.0150 g/cc	0.000542 lb/in ³	On a continuous pre-expander after one expansion
Particle Size	1400 - 2200 µm	1400 - 2200 µm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China