

## Polimeri Europa Flexirene® MS 40 A Linear Low Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Injection Molded

### Material Notes:

Flexirene MS 40 A is a linear low density polyethylene (LLDPE), with antioxidants, suitable for injection molding application. Parts made with Flexirene MS 40 A are characterized by a good balance between impact resistance and rigidity.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polimeri-Europa-Flexirene-MS-40-A-Linear-Low-Density-Polyethylene.php](http://www.lookpolymers.com/polymer_Polimeri-Europa-Flexirene-MS-40-A-Linear-Low-Density-Polyethylene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.930 g/cc	0.930 g/cc	ISO 1183
Melt Flow	27 g/10 min @Load 2.16 kg, Temperature 190 °C	27 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	52	52	ISO 868/A
Tensile Strength at Break	12.0 MPa	1740 psi	ISO 527
Tensile Strength, Yield	11.0 MPa	1600 psi	ISO 527
Elongation at Break	>= 500 %	>= 500 %	ISO 527
Flexural Modulus	0.300 GPa	43.5 ksi	ISO 178

Thermal Properties	Metric	English	Comments
Melting Point	119 °C	246 °F	Internal method
Vicat Softening Point	103 °C @Load 1.00 kg	217 °F @Load 2.20 lb	ISO 306/A
Brittleness Temperature	<= -70.0 °C	<= -94.0 °F	ASTM D746

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China