

Polimeri Europa Greenflex® ML 60 Ethylene Vinyl Acetate Copolymer - Injection Molding, Compounding & Extrusion

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate; Molded/Extruded

Material Notes:

Greenflex ML 60 is an ethylene vinyl acetate copolymer (EVA) for injection molding, compounding and extrusion. Items produced with Greenflex ML 60 show very high elasticity. Main Applications: Greenflex ML 60 is recommended for the production of foamed and crosslinked sheets for shoes and gaskets. Information provided by Polimeri Europa.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-Greenflex-ML-60-Ethylene-Vinyl-Acetate-Copolymer-Injection-Molding-Compounding-Extrusion.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.952 g/cc	0.952 g/cc	ISO 1183
Vinyl Acetate Content	28 %	28 %	Internal Method
Melt Flow	2.5 g/10 min @Load 2.16 kg, Temperature 190 °C	2.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	ISO 868/A
Hardness, Shore D	32	32	ISO 868/A
Tensile Strength, Yield	3.00 MPa	435 psi	ISO 527
Flexural Modulus	0.0100 GPa	1.45 ksi	ISO 178

Thermal Properties	Metric	English	Comments
Melting Point	74.0 °C	165 °F	Internal Method
Vicat Softening Point	44.0 °C @Load 1.00 kg	111 °F @Load 2.20 lb	ISO 306/A
Brittleness Temperature	<= -80.0 °C	<= -112 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China