

Polimeri Europa KOBLEND PCA PD 55 PC+ABS (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Symbol according to ISO 1043/1: PC+ABS Halogen free injection moulding grade with flame retardant properties (UL 94 V-0 at 1.6mm thickness). Main application fields: business machines, electronic and electrical industryUnfilled. Suitable for Injection Molding. Supplied as pellets.ISO data. Information provided by EnichemPolimeri Europa now has Enichem's plastics businesses. This grade is no longer in the product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-KOBLEND-PCA-PD-55-PCABS-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	
Water Absorption	0.40 %	0.40 %	
Melt Flow	28 g/10 min @Load 5.00 kg, Temperature 250 °C	28 g/10 min @Load 11.0 lb, Temperature 482 °F	cm ³ /10 min

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	61.0 MPa	8850 psi	50 mm/min
Elongation at Yield	5.4 %	5.4 %	50 mm/min
Tensile Modulus	2.60 GPa	377 ksi	1 mm/min

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C @Temperature 20.0 °C	38.9 µin/in-°F @Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	103 °C	217 °F	
Deflection Temperature at 1.8 MPa (264 psi)	92.0 °C	198 °F	
Vicat Softening Point	107 °C	225 °F	50°C/hr; 50N
Flammability, UL94	V-0 @Thickness 1.50 mm	V-0 @Thickness 0.0591 in	
	V-0 @Thickness 3.00 mm	V-0 @Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00 \times 10^{15}$ ohm-cm	$\geq 1.00 \times 10^{15}$ ohm-cm	
Surface Resistance	1.00×10^{14} ohm	1.00×10^{14} ohm	
Dielectric Constant	2.9	2.9	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	3.0	3.0	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	30.0 kV/mm	762 kV/in	
Dissipation Factor	0.0050	0.0050	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dissipation Factor	0.0080	0.0080	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	300 V	300 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China