

Polimeri Europa SINKRAL B153/V4 ABS, Heat Stabilized, 17% Glass Fiber (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 20% Glass Fiber Filled

Material Notes:

Symbol according to ISO 1043-1-2: ABS (GF) Grade designation according to ISO 2580-ABS 1, MG, 105-04-09-30, GF15 17% glass fibre reinforced injection moulding grade, with high stiffness and good processing Main applications: Automotive (dashboard inserts, heater ducts) and teletronics (loudspeakers). Filled. Suitable for Injection Molding. Supplied as pellets. Contains lubricant and release agent. ISO data. Information provided by Enichem Polimeri Europa now has Enichem's plastics businesses. This grade is no longer in the product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-SINKRAL-B153V4-ABS-Heat-Stabilized-17-Glass-Fiber-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	
Water Absorption	1.0 %	1.0 %	
Moisture Absorption at Equilibrium	0.20 %	0.20 %	Humidity Absorption
Melt Flow	4.0 g/10 min @Load 10.0 kg, Temperature 220 °C	4.0 g/10 min @Load 22.0 lb, Temperature 428 °F	cm ³ /10 min

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Strength	30.0 kV/mm	762 kV/in	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China