

Polimeri Europa SINKRAL B733/E ABS, Impact & Heat Stabilized Grade (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Extruded

Material Notes:

Symbol according to ISO 1043-1: ABS Grade designation according to ISO 2580-ABS 1,EG,095-04-35-15 Very high impact resistant grade for sheet extrusion with good processability and high thermal stability. Applications: Extrusion of thick sheets (coextruded or not), for sanitary and transportation sectors.Unfilled. Suitable for Profile Extrusion, Sheet Extrusion, Blow Molding, Thermoforming. Supplied as pellets.ISO data. Information provided by EnichemPolimeri Europa now has Enichem's plastics businesses. This grade is no longer in the product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-SINKRAL-B733E-ABS-Impact-Heat-Stabilized-Grade-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	
Water Absorption	1.0 %	1.0 %	
Moisture Absorption at Equilibrium	0.20 %	0.20 %	Humidity Absorption
Melt Flow	3.0 g/10 min @Load 10.0 kg, Temperature 220 °C	3.0 g/10 min @Load 22.0 lb, Temperature 428 °F	cm ³ /10 min

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	39.0 MPa	5660 psi	50 mm/min
Elongation at Break	30 %	30 %	Nominal
Elongation at Yield	3.3 %	3.3 %	50 mm/min
Tensile Modulus	1.80 GPa	261 ksi	1 mm/min
Charpy Impact Unnotched	NB	NB	
	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	3.20 J/cm ²	15.2 ft-lb/in ²	
	2.10 J/cm ²	9.99 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
	90.0 µm/m-°C	50.0 µin/in-°F	

CTE linear, Parallel to Flow			
Thermal Properties	Metric @ Temperature 20.0 °C	English @ Temperature 68.0 °F	Comments
Deflection Temperature at 0.46 MPa (66 psi)	95.0 °C	203 °F	
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	
Vicat Softening Point	99.0 °C	210 °F	50°C/hr; 50N
Glass Transition Temp, Tg	108 °C	226 °F	10°C/min test
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Strength	30.0 kV/mm	762 kV/in	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China