

Polimeri Europa SINKRAL L320/G ABS, Platable Grade (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Plating Grade

Material Notes:

Symbol according to ISO 1043-1: ABS Grade designation according to ISO 2580-ABS 1, MG, 095-25-16-20 Injection moulding grade, tailored for electroplating. It is a high flow grade with a good impact resistance. Applications: Items , even of complex shapes, with high aesthetic aspect for the following sectors: appliances: window frames of washing machines automotive: grilles, car emblems cosmetic: tops. Unfilled. Suitable for Injection Molding. Supplied as pellets. Contains lubricant and release agent. ISO data. Information provided by Enichem Polimeri Europa now has Enichem's plastics businesses. This grade is no longer in the product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-SINKRAL-L320G-ABS-Platable-Grade-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	
Water Absorption	1.0 %	1.0 %	
Moisture Absorption at Equilibrium	0.20 %	0.20 %	Humidity Absorption
Melt Flow	30 g/10 min @Load 10.0 kg, Temperature 220 °C	30 g/10 min @Load 22.0 lb, Temperature 428 °F	cm ³ /10 min

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	43.0 MPa	6240 psi	50 mm/min
Elongation at Break	10 %	10 %	Nominal
Elongation at Yield	3.2 %	3.2 %	50 mm/min
Tensile Modulus	2.30 GPa	334 ksi	1 mm/min
Charpy Impact Unnotched	17.0 J/cm ²	80.9 ft-lb/in ²	
	11.0 J/cm ² @Temperature -30.0 °C	52.4 ft-lb/in ² @Temperature -22.0 °F	
Charpy Impact, Notched	1.80 J/cm ²	8.57 ft-lb/in ²	
	0.700 J/cm ² @Temperature -30.0 °C	3.33 ft-lb/in ² @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 µm/m-°C	50.0 µin/in-°F	

Thermal Properties	@Temperature 20.0 °C Metric	@Temperature 68.0 °F English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	92.0 °C	198 °F	
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	
Vicat Softening Point	97.0 °C	207 °F	50°C/hr; 50N
Glass Transition Temp, Tg	105 °C	221 °F	10°C/min test
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Strength	30.0 kV/mm	762 kV/in	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China