

## Polimeri Europa SINKRAL PD A630/E ABS, Impact & Heat Stabilized Grade (discontinued \*\*)

Category: Polymer, Thermoplastic, ABS Polymer, Acrylonitrile Butadiene Styrene (ABS), Extruded

## **Material Notes:**

Symbol according to ISO 1043-1: ABS Grade designation according to ISO 2580-ABS 1,EG,105-04-35-20 Extrusion grade with very high impact resistance and high glossy aspect. Applications: It is used for the extrusion of pipes, profiles and thin sheets. Unfilled. Suitable for Profile Extrusion. Supplied as pellets. ISO data. Information provided by EnichemPolimeri Europa now has Enichem's plastics businesses. This grade is no longer in the product line.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Polimeri-Europa-SINKRAL-PD-A630E-ABS-Impact-Heat-Stabilized-Grade-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in <sup>3</sup>	
Water Absorption	1.0 %	1.0 %	
Moisture Absorption at Equilibrium	0.20 %	0.20 %	Humidity Absorption
Melt Flow	2.0 g/10 min	2.0 g/10 min	cm³/10 min
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Thermal Properties	Metric	English	Comments
Flammability, UL94	НВ	НВ	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	НВ	НВ	
	@Thickness 3.18 mm	@Thickness 0.125 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Strength	30.0 kV/mm	762 kV/in	
Comparative Tracking Index	600 V	600 V	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com



Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China