

## PolyMirae Moplen 341R Injection Molding Grade Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

**Material Notes:**

Moplen RP341R is the polypropylene random copolymer manufactured by PMC under the license of BASSELL using the Spheripol process. Moplen RP341R is a random copolymer particularly suitable for injection molding of houseware. Moplen RP341R meets the FDA requirement in the code of Federal Regulations in 21 CFR 177.1520. And the components of additives are adequate on the food packaging substances specification of FDA regulation 21 CFR 178.2010. Features: Excellent Transparency; High gloss; Good flowability; Good mechanical property balance Applications: Houseware; Food Container Information provided by PolyMirae Company Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyMirae-Moplen-341R-Injection-Molding-Grade-Polypropylene.php](http://www.lookpolymers.com/polymer_PolyMirae-Moplen-341R-Injection-Molding-Grade-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in <sup>3</sup>	ASTM D1505
Melt Flow	25 g/10 min @Load 2.16 kg, Temperature 230 °C	25 g/10 min @Load 4.76 lb, Temperature 446 °F	Condition L; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	90	90	ASTM D785
Tensile Strength, Yield	31.4 MPa	4550 psi	ASTM D638
Elongation at Yield	8.0 %	8.0 %	ASTM D638
Flexural Modulus	1.27 GPa	185 ksi	ASTM D790
Izod Impact, Notched	0.490 J/cm	0.918 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	95.0 °C	203 °F	ASTM D648
Vicat Softening Point	135 °C	275 °F	ASTM D1525

Optical Properties	Metric	English	Comments
Haze	17 %	17 %	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China