

## PolyMirae Moplen HP525J BDDP Film Grade Polypropylene

Category : Polymer , Film , Thermoplastic , Polypropylene (PP) , Polypropylene, Film Grade

**Material Notes:**

Moplen HP525J is the polypropylene homopolymer manufactured by PMC under the license of BASSELL using the Spheripol process. Moplen HP525J is a homopolymer particularly suitable for Metallizable BOPP (Tender) film. Moplen HP525J resin meets the FDA requirements in the Code of Federal Regulations in 21 CFR 178.2010 for food packaging substances with adequate additives. And contains no dangerous substances according to Federal Regulations in 21 CFR 177.1520. Features: Excellent Processability and stretchability; High Transparency and Gloss; High Stiffness and Strength; Good Barrier Properties; Excellent Metallizability Applications: General purpose film; Metallizable core resin Information provided by PolyMirae Company Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyMirae-Moplen-HP525J-BDDP-Film-Grade-Polypropylene.php](http://www.lookpolymers.com/polymer_PolyMirae-Moplen-HP525J-BDDP-Film-Grade-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in <sup>3</sup>	ASTM D1505
Melt Flow	3.0 g/10 min @Load 2.16 kg, Temperature 230 °C	3.0 g/10 min @Load 4.76 lb, Temperature 446 °F	Condition L; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	98	98	ASTM D785
Tensile Strength, Yield	36.3 MPa	5260 psi	ASTM D638
Elongation at Yield	12 %	12 %	ASTM D638
Flexural Modulus	1.57 GPa	228 ksi	ASTM D790
Izod Impact, Notched	0.490 J/cm	0.918 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	105 °C	221 °F	ASTM D648
Vicat Softening Point	153 °C	307 °F	ASTM D1525

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China