

PolyOne Bergamid™ B70 G30 grey VN7445CF Polyamide 6 (Nylon 6)

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Bergamid-B70-G30-grey-VN7445CF-Polyamide-6-Nylon-6.php

Mechanical Properties	Metric	English	Comments
Tensile Strength	100 MPa	14500 psi	5.0 mm/min; ISO 527
	@Thickness 4.00 mm, Temperature 23.0 °C	@Thickness 0.157 in, Temperature 73.4 °F	
Elongation at Break	3.5 %	3.5 %	5.0 mm/min; ISO 527
	@Thickness 4.00 mm, Temperature 23.0 °C	@Thickness 0.157 in, Temperature 73.4 °F	
Tensile Modulus	6.00 GPa	870 ksi	Injection Molded; ISO 527-2/1
	@Thickness 4.00 mm, Temperature 23.0 °C	@Thickness 0.157 in, Temperature 73.4 °F	
Charpy Impact Unnotched	>= 6.00 J/cm ²	>= 28.6 ft-lb/in ²	Injection Molded; ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.50 J/cm ²	7.14 ft-lb/in ²	Injection Molded; ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB	HB	ALL; Internal Method
	@Thickness 0.800 - 3.00 mm	@Thickness 0.0315 - 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 60093
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	IEC 60093

Descriptive Properties	Value	Comments
Generic Material	Nylon 6	
Generic Name	Polyamide 6 (Nylon 6)	
Regional Availability	Europe	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China