

PolyOne Edgetek® AM-40CF/000 Polyphthalamide (PPA), Carbon Fiber Reinforced (discontinued **)

Category : Polymer , Thermoplastic , Polyphthalamide (PPA)

Material Notes:

Description/Features:Carbon Fiber ReinforcedPolyOne First ChoiceInformation provided by PolyOne Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Edgetek-AM-40CF000-Polyphthalamide-PPA-Carbon-Fiber-Reinforced-nbspdiscontinued.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 g/cc	1.36 g/cc	ASTM D792
Water Absorption	0.10 % @Thickness 3.17 mm	0.10 % @Thickness 0.125 in	24 hr immersion; ASTM D570
Linear Mold Shrinkage	0.0010 - 0.0020 cm/cm	0.0010 - 0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	207 MPa	30000 psi	Type 1 - Rigids, Yield, 0.2 in/min; ASTM D638
Elongation at Break	1.0 - 3.0 %	1.0 - 3.0 %	Type 1 - Rigids, 0.2 in/min; ASTM D638
Tensile Modulus	28.3 GPa	4100 ksi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Flexural Strength	352 MPa	51000 psi	ASTM D790
Flexural Modulus	24.1 GPa	3500 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 3.17 mm, Temperature 23.0 °C	2.00 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Method A, Injection Molded; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	316 °C	600 °F	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	316 - 343 °C	600 - 650 °F	Molding

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China