

PolyOne Edgetek® AS- 08CF / 000 ABS - 8% Carbon Fiber Reinforced With ESD Properties (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 10% Carbon Fiber Filled

Material Notes:

Data provided by PolyOne.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Edgetek-AS-08CF-000-ABS-8-Carbon-Fiber-Reinforced-With-ESD-Properties-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in ³	ASTM D792
Water Absorption	0.25 %	0.25 %	24 hrs. ASTM D570
Linear Mold Shrinkage	0.0025 - 0.0040 cm/cm @Thickness 3.17 mm	0.0025 - 0.0040 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	79.0 MPa	11500 psi	ASTM D638
Elongation at Break	2.0 - 3.0 %	2.0 - 3.0 %	ASTM D638
Tensile Modulus	5.90 GPa	856 ksi	ASTM D638
Izod Impact, Notched	0.640 J/cm @Thickness 6.35 mm	1.20 ft-lb/in @Thickness 0.250 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	99.0 °C	210 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	96.0 °C	205 °F	ASTM D648

Electrical Properties	Metric	English	Comments
Electrical Resistivity	10000 - 1.00e+6 ohm-cm	10000 - 1.00e+6 ohm-cm	ASTM D257
Surface Resistance	10000 - 1.00e+6 ohm	10000 - 1.00e+6 ohm	ASTM D257

Processing Properties	Metric	English	Comments
Melt Temperature	221 - 249 °C	430 - 480 °F	Stock
Mold Temperature			

Processing Properties	27.0 - 54.0 °C Metric	80.6 - 129 °F English	Comments
Drying Temperature	77.0 °C	171 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China