

PolyOne Edgetek® AS-30GF/000 Acrylonitrile Butadiene Styrene (ABS), Glass Filled (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

Description/Features: Glass Fiber Reinforced PolyOne First Choice Information provided by PolyOne Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Edgetek-AS-30GF000-Acrylonitrile-Butadiene-Styrene-ABS-Glass-Filled-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.274 g/cc	1.274 g/cc	ASTM D792
Water Absorption	0.20 %	0.20 %	24 hr. Immersion, -; ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0025 cm/cm	0.0020 - 0.0025 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	79.3 MPa	11500 psi	Type 1 - Rigids, Break, 0.2 in/min; ASTM D638
Elongation at Break	3.0 %	3.0 %	Type 1 - Rigids, 0.2 in/min; ASTM D638
Tensile Modulus	6.55 GPa	950 ksi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Flexural Strength	100 MPa	14500 psi	ASTM D790
Flexural Modulus	6.55 GPa	950 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Thickness 6.35 mm, Temperature 23.0 °C	1.50 ft-lb/in @Thickness 0.250 in, Temperature 73.4 °F	Method A, Injection Molded; ASTM D256

Processing Properties	Metric	English	Comments
Melt Temperature	221 - 243 °C	430 - 470 °F	Molding
Mold Temperature	65.6 °C	150 °F	
Drying Temperature	65.6 °C	150 °F	2 hrs

Descriptive Properties	Value	Comments
Product Form	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China